

Nedal Aluminium BV

Groenewoudsedijk 1 3528 BG Utrecht P.O. Box 2020 3500 GA Utrecht The Netherlands +31 (0)30 292 57 11 info@nedal.com www.nedal.com

ALLOY DATA SHEET EN-AW 6082[AIMgSi] (Type: High strength structural alloy)

The alloy EN AW-6082 is a high strength extrusion alloy for highly loaded structural applications. Typical applications are scaffolding elements, rail coach parts, offshore constructions, containers, machine building and mobile cranes. Due to the fine grained structure this alloy exhibits a good resistance to dynamic loading conditions. EN AW-6082 is certified for use in marine applications

Chemical composition according to EN573-3 (weight%, remainder AI)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	remarks	others	
									each	total
0.70-	max.	max.	0.40-	0.6-	max.	max.	max.		max.	max.
1.3	0.50	0.10	1.0	1.2	0.25	0.20	0.10		0.05	0.15

Mechanical properties according to EN755-2

rechanical properties according to En755 2								
Temper*	Wallthickness e*** [mm]	Yield stress Rp _{0.2} [MPa]	Tensile strength Rm [MPa]	Elongation A A ₅₀ [%] [%]		Hardness** HB		
T4	≤ 25	110	205	14	12	65		
T5	≤ 5	230	270	8	6	80		
Т6	≤ 5	250	290	8	6	95		
10	5 < e ≤ 25	260	310	10	8	95		

*Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged, (T6 properties can be achieved by press quenching)

** Hardness values are for indication only

***For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section

Physical properties (approximate values, 20°C)

Density	Melting range	Electrical	Thermal	Co-efficient of	Modulus of		
		Conductivity	Conductivity	thermal	Elasticity		
[kg/m ³]	[°C]	[MS/m]	[W/m.K]	Expansion	[GPa]		
				10 ⁻⁶ /K			
2700	585-650	24-32	170-220	23.4	~70		

Weldability¹

Gas: 3 TIG: 2 MIG: 1

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or SG-Al4.5Mn0.7(A) or AlSi5. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹ Coating properties¹ T4 temper: 4 T5 and T6 temper: 2 Hard protecting anodising: 2 Decorative/bright/colour anodising: 3 Corrosion resistance¹ Formation of the second second

General: 2 Marine: 2

¹Relative qualification ranging from 1-very good to 6 unsuitable

February 2018 Rev. 02

